

FIBRE OPTIC CABLES

MICRO singlemode


SXKO-MICRO-144-OS-HDPE



Outer jacket	HDPE, reaction to fire F _{ca}
Cable secondary protection	gel-filled tube
Cable type acc. to the number of tubes	MLT
Operating temperature	-30 to +70 °C
Installation temperature	-15 to +50 °C
Storage temperature	-4 to +70 °C
Fibre type	G.657A1 OS2
Diameter of the primary protection	12-96f: 250 µm, 144f: 200 µm
Short-term tensile resistance	12-60f: 430 N, 72f: 900 N, 96f: 1 500 N, 144f: 900 N
Short-term pressure resistance	12-96f: 700 N/10 cm 144f: 500 N/10 cm
Minimum bend radius (short term)	20x D cable
Minimum bend radius (long-term)	10x D cable
Cable diameter	12-60f: 5,3 mm, 72f: 5,7 mm, 96f: 6,5 mm, 144f: 5,8 mm
Cable weight	12f: 19 kg/km, 24f: 21 kg/km, 48f: 23 kg/km, 60f: 24 kg/km 72f: 29 kg/km, 96f: 41 kg/km, 144f: 31 kg/km
The number of fibres in the tube	12-96f: 12, 144f: 24

Solarix MICRO air blow-in fibre optic cables SXKO-MICRO-OS-HDPE reaction to fire F_{ca} are suitable for blowing into micro tubes and HDPE tubes thanks to the high viscosity HDPE jacket that allows the cable to slide easily along the inner side of the tube. The fibres themselves are stored in a gel-filled tube to protect them from moisture. There are 12 fibres stored in each tube in the 12-96f version and 24 fibres in the 144f version. The primary fibre protection used has a standard diameter of 250 µm, and reduced protection of 200 µm for 144f cable. The fibre optic cable has no metallic elements and is fully dielectric. The fibre itself is of the G.657A1 OS2 type.

Part No.	Description
SXKO-MICRO-12-OS-HDPE	Air blow-in cable MICRO Solarix 12f 9/125, HDPE, black
SXKO-MICRO-24-OS-HDPE	Air blow-in cable MICRO Solarix 24f 9/125, HDPE, black
SXKO-MICRO-48-OS-HDPE	Air blow-in cable MICRO Solarix 48f 9/125, HDPE, black
SXKO-MICRO-72-OS-HDPE	Air blow-in cable MICRO Solarix 72f 9/125, HDPE, black
SXKO-MICRO-96-OS-HDPE	Air blow-in cable MICRO Solarix 96f 9/125, HDPE, black
SXKO-MICRO-144-OS-HDPE	Air blow-in cable MICRO Solarix 144f 9/125, HDPE, black



- Cable construction
1. Fibres
 2. Gel-filled tube
 3. Strength member
 4. Filling tube
 5. Water-proof tape
 6. Aramid yarn
 7. Rip cord
 8. Outer jacket

SXKO-MICRO-72-OS-HDPE



+420 840 505 555 • info@solarix.cz
www.solarix.cz



FIBRE OPTICS

Optical Fibres Parameters

Singlemode Fibres Basic Parameters

Geometric Parameters	Unit	ITU-T G.652.D	ITU-T G.657.A1	ITU-T G.657.A2
Mode Field Diameter (MFD)				
@ 1 310 nm	µm	9,2 ± 0,4	8,9 ± 0,4	8,6 ± 0,4
@ 1 550 nm	µm	10,4 ± 0,5	10,1 ± 0,5	9,6 ± 0,4
Cladding diameter	µm	125 ± 0,7	125 ± 0,7	125 ± 0,7
Coating diameter - fiber 200 µm	µm	242 ± 5,0 (uncolored)	242 ± 5,0 (uncolored) 185 ± 5,0 (uncolored)	242 ± 5,0
Core-Cladding Concentricity Error	µm	≤ 0,5	≤ 0,5	≤ 0,5
Cladding-Coating Concentricity Error	µm	≤ 12	≤ 12	≤ 12
Transmission Parameters				
Attenuation				
@ 1 310 nm	dB/km	0,32 - 0,36 ¹⁾	0,32 - 0,36 ¹⁾	0,32 - 0,36 ¹⁾
@ 1 550 nm	dB/km	0,19 - 0,24 ¹⁾	0,19 - 0,24 ¹⁾	0,19 - 0,24 ¹⁾
@ 1 625 nm	dB/km	0,22 - 0,26 ¹⁾	0,22 - 0,26 ¹⁾	0,22 - 0,26 ¹⁾
Dispersion Coefficient				
@ 1 550 nm	ps/(nm*km)	≤ 18	≤ 18	≤ 18
@ 1 625 nm	ps/(nm*km)	≤ 22	≤ 22	≤ 22
PMD individual fibre	ps/√km	0,1	0,1	0,1
Cable Cutoff Wavelength λ _{cc}	nm	≤ 1 260	≤ 1 260	≤ 1 260
Fibre Cutoff Wavelength λ _c	nm	1 150 - 1 330	1 150 - 1 330	1 150 - 1 330

¹⁾ A typical value for fibres in loose tube cables.

Multimode Fibres Basic Parameters

Geometric Parameters	Unit	ITU-T G.651.1 OM2	ITU-T G.651.1 OM3	ITU-T G.651.1 OM4	ITU-T G.651.1 OM5
Core diameter	µm	50 ± 2,5	50 ± 2,5	50 ± 2,5	50 ± 2,5
Cladding diameter	µm	125 ± 1,0	125 ± 1,0	125 ± 1,0	125 ± 1,0
Core-Cladding Concentricity Error	µm	≤ 1,5	≤ 1,0	≤ 1,0	≤ 1,0
Cladding-Coating Concentricity Error	µm	≤ 10,0	≤ 10,0	≤ 10,0	≤ 10,0
Transmission Parameters					
Numerical aperture	-	0,200 ± 0,015	0,200 ± 0,015	0,200 ± 0,015	0,200 ± 0,015
Attenuation					
@ 850 nm	dB/km	2,2 - 3,5 ¹⁾	2,2 - 3,5 ¹⁾	2,2 - 3,5 ¹⁾	2,2 - 3,0 ¹⁾
@ 1 300 nm	dB/km	0,5 - 1,5 ¹⁾	0,5 - 1,5 ¹⁾	0,5 - 1,5 ¹⁾	0,5 - 1,5 ¹⁾
Bandwidth					
@ 850 nm	MHz*km	≥ 500	≥ 1 500	≥ 3 500	≥ 3 500
@ 953 nm	MHz*km	-	-	-	≥ 1 850
@ 1 300 nm	MHz*km	≥ 500	≥ 500	≥ 500	≥ 500

¹⁾ A typical value for fibres in loose tube cables.

FIBRE OPTICS

Color Coding for Fibres and Tubes

Fibres Color Coding

Fibre	1	2	3	4	5	6	7	8	9	10	11	12
Colour	blue	orange	green	braun	grey	white	red	black	yellow	purple	pink	turquoise
Fibre	13	14	15	16	17	18	19	20	21	22	23	24
Colour ¹⁾	blue	orange	green	braun	grey	white	red	black	yellow	purple	pink	turquoise

¹⁾ Colour with a strip

Tubes Color Coding for MLT Cables

Tube	1	2	3	4	5	6	7	8	9	10	11	12
Colour	blue	orange	green	braun	grey	white	red	black	yellow	purple	pink	turquoise

Tubes Color Coding for MLT Cables

Tube	1	2	3	4
Colour	red	green	natural	natural